

Solvent-based Screen Printing Ink for the manufacturing of ID-Cards

Suitable for laminating and embossing, off-set-overprintable, satin ink film, very flexible

Vers. 7
2014
14. Jan

Field of Application

Substrates

Maraflex FX is a solvent based screen printing ink suitable for printing onto

- PVC films
- rigid PVC
- extruded ABS blanks

Since all the print substrates mentioned may have differing printability characteristics, even within an individual type, preliminary trials are essential to determine suitability for the intended use.

Field of use

Maraflex FX is suitable for printing on single and multi-layered identity cards such as customer loyalty cards, club cards, bank cards, telephone cards, smart cards, or ID system cards. FX excels through particularly good laminating characteristics. FX can also be used in combination with other printing methods such as waterless or UV offset as well as subsequent processing methods like press finishing.

Attention:

The colour shade FX 170 opaque white is not suitable for laminating.

Characteristics

The FX colour shades are brilliant with medium opacity. This ensures excellent lamination (except for FX 170 opaque white) with high outputs and allows the mixing of very pure colour shades.

Ink Adjustment

The ink should be stirred homogeneously before printing and if necessary during production.

Drying

Physically very fast drying; dries at 20°C ambient temperature within 10 min. ready for overprinting, at 50°C in a tunnel dryer (2 warm – 1 cold section) within 30 - 40 sec.

The times mentioned above vary according to the substrate, the ink film thickness, drying conditions and the auxiliaries used.

When overprinting the ink an extended drying time is necessary due to the solvent retention of the previously printed colour.

When overprinting, an increased drying time is required due to the rewetting of the previous print layer. When printing both sides of cards, careful checks are necessary, so as to ensure adequate block resistance.

Good final drying properties and a check for residual solvents in the printed ink film are essential for successful lamination, good overprintability, and high peel resistance. Here, "Wicket" dryers have proven to be most effective, due to the long dwell time of 10-20 min. in the tunnel. Too much residual solvent content in the ink generally degrades the laminating result.

Fade resistance

Pigments of excellent fade resistance (blue wool scale 6-8) are used for our ink series Maraflex FX.

Stress resistance

After proper and thorough drying, the ink film is very flexible and laminable. Furthermore, its surface is resistant to scratching and bending.

Due to the gloss levels required for good offset overprintability, the dry abrasion and rub resistance properties are somewhat lower.

Maraflex FX shows good resistance against alcohol and finger sweat.



Range

Basic Shades

| | |
|-----|------------------|
| 920 | Lemon |
| 922 | Light Yellow |
| 924 | Medium Yellow |
| 926 | Orange |
| 930 | Vermilion |
| 932 | Scarlet Red |
| 934 | Carmine Red |
| 936 | Magenta |
| 940 | Brown |
| 950 | Violet |
| 952 | Ultramarine Blue |
| 954 | Medium Blue |
| 956 | Brilliant Blue |
| 960 | Blue Green |
| 962 | Grass Green |
| 970 | White |
| 980 | Black |

Transparent Shades

| | |
|-----|--------------------|
| 520 | Transparent Yellow |
| 536 | Transparent Red |

Press-Ready Metallics

| | |
|-----|---------------|
| 191 | Silver |
| 195 | Fine Silver |
| 197 | Medium Silver |
| 199 | Coarse Silver |

Further Products

| | |
|-----|-------------------|
| 170 | Opaque White |
| 903 | Offset Base |
| 904 | Special Binder |
| 910 | Overprint Varnish |

All shades are intermixable. Mixing with other ink types or auxiliaries must be avoided in order to maintain the special characteristics of this outstanding ink range.

All basic shades are included in our Marabu-ColorFormulator (MCF). They build the basis for the calculation of individual colour matching formulas, as well as for shades of the common colour reference systems HKS®, PANTONE®, and RAL®. All formulas are stored in the Marabu-Color Manager software.

Due to the high amount of pigments contained, FX 170 opaque white cannot be laminated.

Libramatt LIM 170 can be used for signature fields.

Metallic Mixing System

Metallic colour shades on ID cards are a core strength of screen printing. Thanks to the Marabu Metallic Mixing System including 4 silver shades with different pigment sizes, 2 transparent shades, and 17 FX standard shades almost any metallic hue can be mixed.

| | | |
|--------|--|----------------------|
| FX 191 | Metallic-Silver, medium like FX 197 but more transparent | Mesh 77-55 to 90-48 |
| FX 195 | Metallic-Silver, fine | Mesh 90-48 to 100-40 |
| FX 197 | Metallic-Silver, medium | Mesh 77-55 to 90-48 |
| FX 199 | Metallic-Silver, coarse | Mesh 43-80 |

All mixed metallic shades can be laminated and are storable for 1 year.

Auxiliaries

| | | |
|-------|---------------------|--------|
| UKV 1 | Thinner, fast | 10-15% |
| UKV 2 | Thinner | 10-15% |
| UR 3 | Cleaner (flp. 42°C) | |
| UR 4 | Cleaner (flp. 52°C) | |
| UR 5 | Cleaner (flp. 78°C) | |
| SV 5 | Retarder, fast | |
| SV 10 | Retarder, slow | |

Thinner is added to the ink to adjust the printing viscosity. For slow printing sequences and fine motifs, it may be necessary to add retarder to the thinner (max. 1:1). To ensure good laminating characteristics, no other auxiliaries should be added to the FX.

The cleaners UR 3 and UR 4 are recommended for manual cleaning of the working equipment.

Cleaner UR 5 is recommended for manual or automatic cleaning of the working equipment.

Printing Parameters

All types of commercially available fabrics and solvent-resistant stencils can be used. The fabric recommendation for standard shades is 90-48 to 120-34, for metallics please refer to the chapter Metallic Mixing System.

Laminating parameters

The following laminating parameters have proven to work for PVC on the market.

Laminating temperature: 140°C to 150°C

Pressure: 1 ton for sheet sizes of 35x50cm

Laminating time: approx. 15 min

Note

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor their suitability for each application.

You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us and utilised by you with respect to any and all damages not caused intentionally or by gross negligence.

Labelling

For Maraflex FX and its additives and auxiliaries, there are current Material Safety Data Sheets available according to EC regulation 1907/2006, informing in detail about all relevant safety data including labelling according to the present EEC regulations as to health and safety labelling requirements. Such health and safety data may also be derived from the respective label.